



HYBRID

MULTIPOLYMER COAT

EXTERIOR



water resistant



sun resistant



fire resistant



fast drying



 **Linton**

COATING TECHNOLOGY

34-300 Żywiec, ul. Zielona 8 POLAND
www.linton.pl
phone: +48 516 145 175



Hybrid Multipolymer Coat.

The coat is intended for coating architectural profiles using a device called the PERFECT COATING.

The hybrid coating of polymer compound containing silica sand. For exterior use. Highly flexible. Water and sun resistant.

Very good resistance to sunlight, very low water absorption and very high water resistance.

The layer thickness up to 3 mm

Density: 1.7-1.9 g/cm³

Graining up to 0.4 mm

Drying temperature: 15°C -30°C

Storage temperature: 5°C -40°C

The maximum total quantity that can be mixed: 350 kg

The manner of use.

Stir the product before use as recommended by the manufacturer.

Mixing time for a bucket with 35 kg HYBRID mass - 4 minutes at a speed of 650 rpm with a 18 cm diameter vaned disk.

Mixing time for a tune with 350 kg HYBRID mass-10-12 minutes at a speed of 650 rpm with a 24 cm diameter vaned disk. The coating should be applied undiluted!

Work in substrate and ambient temperature between 10°C and 30°C on a non-sunny surface, on days free from rain and fog.

Clean the machine and tools with tap water immediately after completing the work.

Storage:

In unopened packages, the product retains its properties for 6 months from the date of production. Store between 10°C and 40°C in factory-sealed packages.

Protect from frost and excessive sunlight!

The coating is a non-flammable product.

Hazard classification:

S 2 Keep out of the reach of children

S 20 When using do not eat or drink

S 24 Avoid contact with skin

S 25 Avoid contact with eyes

S 26 In case of contact with eyes, rinse immediately with plenty of water and seek medical advice

S 27 Take off immediately all contaminated clothing

S 28 After contact with skin, wash immediately with plenty of soapy water

S 40 To clean the floor and all objects contaminated by this material use plenty of soapy water

S 45 In case of accident or if you feel unwell seek medical advice immediately

Manufacturer:

LINTON

34-300 ywiec ul. Zielona 8 POLAND; tel. +48 516 145 175

e-mail: biuro@linton.pl

www.linton.pl